



Precision Board Plus™

PBLT-60

DESCRIPTION & APPLICATION:

PBLT-60 is a rigid, high density urethane (HDU) Tooling/Modeling board designed for Prototype Machining, Pattern Making, Thermoforming, Prepreg Composite Layup Tooling, Vacuum Form Tooling, Tool Proofing, Master Model Making, Indoor & Outdoor Signage. PBLT Plus is made in USA.

Precision Board Plus PBLT is formulated with eco-friendly, "Green" urethane components. The new Plus formulations have achieved a Certified "Carbon Balance" of 3 to 1 and a Certified "Rapidly Renewable Green Resource Content" of 18.9%. Assists meeting LEED requirements for obtaining USGBC and ICC 700 building credits. PBLT Plus has a tighter cell structure, which now results in more chips and less dust during cutting and machining.

Precision Board Plus **does not contain: CFC's or VOC's** See MSDS for details

Precision Board Plus PBLT comes in standard sizes of 20"x60", 24"x60", 30"x80", 4'x8', 4'x10', 5'x8' and 5'x10'. Thickness ranges from 1/2" to 24". Other special sizes and custom bonded shapes are available upon request. Standard densities are available in 4, 6, 8, 10, 12, 15, 18, 20, 30, 34, 40, 48 and 60 pounds per cubic foot (pcf). Other special densities are available.

Precision Board PBLT is **non-abrasive** and can be machined and cut with HSS cutters, or any standard cutting tool. PBLT Plus does not outgas or affect prepreg resin cure. **See FAQ for important oven/autoclave ramping procedures and other pertinent information.**

PBLT can be bonded to itself or most other substrates using Coastal Enterprises' single component urethane adhesives: PB Bond-240 and PB Fast Set, or EP-76, two part, epoxy adhesive.

PHYSICAL PROPERTIES:

Density	ASTM D-1623	60 lbs/Cubic Foot
Compressive Strength	ASTM D-1621	4,760 psi
Compressive Modulus	ASTM D-1621	84,320 psi
Tensile Strength	ASTM D-1623	2,410 psi
Tensile Modulus	ASTM D-1623	47,798 psi
Shear Strength	ASTM C-273	790 psi
Shear Modulus	ASTM C-273	8,735 psi
Flexural Strength Method 1A	ASTM D-790	3,860 psi
Flexural Modulus Method 1 A	ASTM D-790	240,503 psi
Hardness	Shore D	80.5
Elongation		6.2%
Dimensional Stability	ASTM D-2126	1.2% Max.
Water Absorption	ASTM D-2842	0.03% by Vol. after 96 hrs.
Closed Cell Content	ASTM D-2856	97%
"K" Value Insulation Factor	ASTM C-177	1.19
Impact Resistance	0°F 4.6 oz. 1" Dia. 9/6" drop	No cracking observed
Freeze Thaw	ASTM D-2126, 25 Cycles	No disbonding or distortion occurred
Mold and Mildew Resistance	ASTM D-3273	Does not support growth
Dielectric Constant	ASTM D-1678	1.3
Maximum Service Temperature	Dry	200° F
Coefficient of Thermal Expansion (CTE)		25 X 10 ⁻⁶ °F
Glass Transition	DMA	218°F
Specific Heat @ 77°F	ASTM E-1269	0.353
Precision Board does not contain:	Chlorinated Fluorocarbons (CFC's) or Volatile Organic Compounds (VOC's)	
Flammability Tests:	FAR 25.853 Vertical Burn	Pass
	MIL P 26514 Burn Test	Pass
	ASTM D-1692-74 Burn Test	Pass
	ASTM D635-06	Pass

Follow heat temperature ramping of 1°F up per minute & 2°F down per minute. See FAQ for additional data.

Any Questions please contact Coastal Enterprises Company

(800) 845-0745

www.PrecisionBoard.com

WARRANTY: All recommendations for product use have been derived from experience and test data believed to be reliable. We warrant and guarantee the uniformity of our products within manufacturing tolerance. However, since the use of our products is beyond our direct control, they are furnished upon the condition that each party shall make his/her own tests to determine their suitability for his/her particular purpose. Except as stated herein, Coastal Enterprises Company makes no warranty or guarantee, expressed or implied, and disclaims all responsibility for results obtained, nor assumes any liability for any damages, whether arising out of negligence or breach of guarantee and is hereby expressly limited to replacement of product only. For additional information on product handling, please refer to Precision Board Plus MSDS.